

PRODUCT DESCRIPTION

Stonchem 441LV is a 100% solids polyurea-polyurethane hybrid lining system applied at a nominal thickness of 30 to 120 mil/0.75 to 3.0 mm, depending on conditions of use. This immersion-grade lining provides a durable, flexible, waterproof membrane that can withstand significant impact and abrasion. This system can be applied over a broad range of substrates and in varied environmental conditions. Stonchem 441LV has very good resistance to petroleum products, caustics and moderate concentrations of acids.

USES, APPLICATIONS

- Wastewater treatment/storage
- Secondary containment areas
- Bulk tank farms
- Waterproofing
- Tank liners
- Scrubber decks
- Chutes
- Mechanical rooms
- Helicopter decks
- Refrigerators/freezers
- Truck loading ramps
- Mezzanines
- Interior walls and ceilings
- Laboratories

PRODUCT ADVANTAGES

- 100% solids (solvent-free)
- Superior abrasion resistance
- Seamless and monolithic
- Suitable for a broad range of substrates
- Watertight
- Can be applied in cold environments
- Excellent crack bridging capabilities

CHEMICAL RESISTANCE

Stonchem 441LV is formulated to resist a variety of chemical solutions. Refer to the Stonchem 400 Series Chemical Resistance Guide, which lists reagent concentration and temperature recommendations.

PACKAGING

Stonchem 441LV is packaged in units for easy handling. Each unit consists of:

Stonchem 441LV

6-gallon unit:

1 carton containing:

6 foil bags of Isocyanate

1 carton containing:

6 poly bags of Polyol/Amine

COVERAGE

Each mix of Stonchem 441LV is approximately one gallon. One gallon of Stonchem 441LV will cover approximately 1,600 sq. ft./149 sq. m per mil of application thickness. Coverage per gallon for typical thicknesses are as follows:

<u>Thickness</u>	<u>Application Coverage</u>
30 mil	53 sq. ft./5.0 sq. m
50 mil	32 sq. ft./3.0 sq. m
120 mil	13 sq. ft./1.2 sq. m

STORAGE CONDITIONS

Store all components of Stonchem 441LV between 60 to 85°F/13 to 30°C in a dry area, out of direct sunlight. BE SURE TO HANDLE AND STORE PROPERLY. The shelf life is 2 years in the original, unopened container.

PHYSICAL CHARACTERISTICS

Tensile Strength (ASTM D-638)	3,000 psi
Elongation (ASTM D-638)	140%
Hardness (ASTM D-2240, Shore D)	60
Abrasion Resistance (ASTM D-4060, CS-17)	0.035 gm max. weight loss
Low Temperature Flexibility Test (ASTM D-522)	-10°F/-23°C Pass
VOC (ASTM D-2369, Method E)	2 g/l
Cure Rate	8 hours for foot traffic 24 hours for chemical or immersion
Color	Light Gray

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual system, including binder and filler, were used as test specimens.

SUBSTRATE

Stonchem 441LV, with the appropriate primer, is suitable for application over concrete, wood, brick, quarry tile, metal or Stonhard mortar systems. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

PRIMING

Stonchem Epoxy Primer must be applied to the prepared surface and cured to a tack-free state before applications of the Stonchem 441LV begins. For outgassing substrates, a second coat of primer may be applied. The primer can be thickened by adding Stonchem Thixotrope. The use of a primer seals the substrate and enhances bonding. The primer should be applied using a rubber squeegee.

Note: Primer should be applied later in the day as the substrate begins to cool.

APPLICATION GUIDELINES

For optimal working conditions, substrate temperature must be from 60 to 80°F/15 to 27°C. Cold areas must be heated until the slab temperature is above 55°F/13°C to ensure the material achieves a proper cure. A cold substrate will make the material stiff and difficult to apply. Warm areas or areas in direct sunlight must be shaded or arrangements made to work during evenings or at night. A warm substrate (60 to 80°F/15 to 27°C) will aid in the material's workability; however, a hot substrate (80 to 90°F/27 to 32°C) or a substrate directly in the sun will shorten the material's working time and can cause other phenomenon such as pinholing and bubbling. Substrate temperature should be greater than 5°F/3°C above dew point.

Application and curing times are dependent upon ambient and surface conditions. Consult Stonhard's Technical Service Department if conditions are not within recommended guidelines.

APPLYING STONCHEM 441LV

1. Combine one bag of isocyanate and one bag of polyol in a 5-gallon pail and mix for 90 seconds with slow-speed drill and mixing blade. Do not mix more than three mixes at one time.
2. Pour the material onto the floor in the form of a bead along the farthest wall from the mixing area. Using a 30 mil notched squeegee held at a 45° angle to the bead, apply the 441LV by pulling the squeegee along the bead and working the material back toward the mix area. Each pass should overlap the last by nine inches to ensure that all substrate voids are filled.
3. Wearing spiked shoes, roll the 441LV using a nap roller to remove squeegee lines.

CURING

The surface of Stonchem 441LV will be tack-free in 8 hours at 70°F/21°C. The coated area may be put back into service in 24 hours at 70°F/21°C, conditions permitting.

PRECAUTIONS

- Acetone is recommended for cleanup of Stonchem 441LV isocyanate or polyol/amine resin material spills. Use these materials only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- Avoid contact with Stonchem 441LV polyol resin and isocyanate, as they may cause skin, respiratory and eye irritation.
- The use of NIOSH/MSHA approved respirators using an organic vapor/acid gas cartridge is mandatory during spray applications.
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles or safety glasses and impermeable gloves are required.
- In the event of accidental eye contact, immediately flush eyes with copious amounts of water for 15 minutes and seek medical attention.
- If material is ingested, immediately contact a physician. DO NOT INDUCE VOMITING.
- Use only with adequate ventilation. Inhalation of vapors may cause severe headaches, nausea and possibly unconsciousness.

NOTES

- Material Safety Data Sheets for Stonchem 441LV are available on line at www.stonhard.com under Products or upon request.
- Specific information regarding the chemical resistance of Stonchem 441LV is available in the Stonchem 400 Series Chemical Resistance Guide.
- A staff of technical service engineers is available to assist with product application, or to answer questions related to Stonhard products.
- Requests for technical service or literature can be made through local sales representatives and offices or corporate offices located worldwide.

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

04/25

© 2025 Stonhard www.stonhard.com



USA HQ	(800) 257 7953	Mexico	+(52) 55 9140 4500	Belgium	+(32) 67 49 37 10	South Africa	+(27) 11 254 5500	Australia	+(61) 3 9587 7433
Canada	(800) 263 3112	Argentina	+(54) 11 5032 3113	Dubai, UAE	+(971) 4 3470460	India	+(91) 22 28500321		