STONCLAD UF

PRODUCT DESCRIPTION

Stonclad UF is a four-component, textured, hand-trowel applied, polyurethane mortar system. Stonclad UF consists of a urethane urea binder, pigments, and an aggregate blend of flint and graded quartz aggregates. Stonclad UF can be applied at thicknesses ranging from 1/4 to 3/8 inches depending on application requirements. Stonclad UF is a high-impact-resistant mortar which exhibits excellent abrasion, thermal-shock, thermal-cycling, and chemical-resistant characteristics, making it ideal for the food and beverage industry or any other applications requiring these properties. It cures to an impervious surface requiring no additional sealer. Additionally, Stonclad UF is self-priming, making it ideal for quick installations to minimize down-time.

SYSTEM OPTIONS

Waterproofing

Where the total system must be waterproof, use of Stonhard's Stonproof ME7 membrane system with texture #3 broadcast to refusal is required with strict adherence to application instructions.

Cove Base

To provide an integral seal at the joint between the floor and the wall, cove bases in heights from 2 to 6 inches are available.

Crack Treatment

When crack treatment is needed due to cracks in the substrate, the use of Stonhard's Stonproof CT5 or RH7 with texture #3 broadcast to refusal is required with a strict adherence to application instructions.

Note: Stonproof materials must fully cure before applying Stonclad UF.

Texture

The default level of finished texture can be adjusted based on the area's intended use. Wet areas will receive a higher level of texture, whereas dry areas can receive a less textured finish. The level of texture is determined through application techniques. No additional materials are needed to achieve these textures. Note that with increased texture comes a general decrease in "cleanability" of the floor. It is important to find the necessary balance between slip resistance and cleanability for each installation.

PACKAGING

Stonclad UF is packaged in units for easy handling. Each unit consists of:

Stonclad UF AB

4 cartons of Stonclad UF AB, each containing:4 foil bags of isocyanate4 poly bags of polyol

16 individual bags of Part C-1 aggregate

1.3 cartons of Stonclad C-2 pigment, containing:12 bags of Part C-2 powdered pigment packs

COVERAGE

Each unit of Stonclad UF will cover approximately 200 sq.ft. of surface at a nominal 1/4 inch thickness.

PHYSICAL CHARACTERISTICS

(ASTM C-579)	6,200 psi after 7 days 870 psi
(ASTM C-307)	
	2,500 psi
(ASTM C-580)	
(ASTM D-4060, CS-17)	400 : ///
(ASTM D-2794)	Class 1
(ASTM E-648)	Class 1
Coefficient of Thermal Expansion	
•	1.7 x 10 ^{-₅} m/m°C
(ASTM C-531)	
· /	11 g/l
(ASTM D-3960)	3
Cure Rate	
(@ 77°F)	24 hours for normal operations

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab-made test coupons.

STORAGE CONDITIONS

Store all components of Stonclad UF between 60 to 85°F in a dry area. Avoid excessive heat and do not freeze. The shelf life of the liquids is one year while the C-1 aggregate has a 6-month shelf life each in their original, unopened containers.

COLOR

Stonclad UF is available in 10 standard colors. Refer to the Stonclad Color Sheet for more information. Contact your local Stonhard representative with any questions.

SUBSTRATE

Stonclad UF, in conjunction with an appropriate primer where necessary, is suitable for application over properly prepared concrete, wood, brick, quarry tile, metal, or Stonset TG6. For questions regarding other substrates or an appropriate primer, contact your local representative or technical service.

Note: Stonclad UF is suitable for application over new/green concrete. The concrete must be in place for a minimum of 5 days, have a vapor barrier installed beneath it, be sufficiently dry, and have achieved enough strength to handle mechanical preparation.

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or technical service.

PRIMING

Stonclad UF is a self-priming system over concrete in good condition. For rougher concrete, the use of primer is necessary. Questions regarding the necessity of primer should be directed to Stonhard technical service.

MIXING

Proper mixing is critical for the product to exhibit the proper application properties, cure properties, and ultimate physical properties. Mechanical mixing using a JB Blender (or equivalent 5-gallon pail mixer) or a larger mortar mixer (e.g., a Baugh 3 Batch mixer) is required. See Stonclad UF Directions for further details.

APPLYING

- DO NOT attempt to install material if the temperatures of Stonclad UF components are not within 60 to 77°F and substrate/air temperatures are not within 45 to 77°F. The cure time and application properties of the material are severely affected in temperatures outside these ranges.
- For applications below 60°F or above 77°F please contact Stonhard technical service for additional installation information and advice.
- Material must be applied immediately after mixing.
- If primer is being used, mix and apply the primer to the floor and allow it to fully cure (6-8 hours) before application of Stonclad UF.
- Stonclad UF is hand-trowel applied. Avoid over-working or polishing the material to ensure texture remains consistent throughout the floor.
- Detailed instructions on application and installation techniques can be found in the Stonclad UF Directions.

PRECAUTIONS

- Use these materials only in strict accordance with the manufacturer's recommended safety procedures. Dispose of waste materials in accordance with government regulations.
- The selection of proper protective clothing and equipment will significantly reduce the risk of injury. Body covering apparel, safety goggles or safety glasses, and impermeable gloves are required.
- In case of contact, flush area with water for 15 minutes and seek medical attention. Wash skin with soap and water.
- If material is ingested, immediately contact a physician. DO NOT INDUCE VOMITING.
- During prep-work of floor substrate or mixing of Stonhard product while adding aggregate, dust masks must be worn.
- Use only with adequate ventilation.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stonclad Chemical Resistance Guide.
- Safety Data Sheets for Stonclad UF are available online at www.stonhard.com or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related to Stonhard products.
- Requests for literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall, and lining systems will change over time due to normal wear, abrasion, traffic, and cleaning. Generally, high-gloss coatings are subject to a reduction in gloss, while matte-finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly, and deep cleaned periodically, to ensure no contaminant buildup occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require tractionenhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use.

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.





Australia

USA HQ Canada (800) 257 7953 Mexico (800) 263 3112 Argentina +(52) 55 9140 4500 +(54) 11 5032 3113 Belgium Dubai, UAE +(32) 67 49 37 10 +(971) 4 3470460 South Africa India

+(27) 11 254 5500 +(91) 22 28500321 +(61) 3 9587 7433